

Index

GROUP 1 Ordinary Grades

GROUP 2 Medium Grades

GROUP 3 High Grades

GROUP 4 Kraft Grades

GROUP 5 Special Grades



EU PAPER TYPES

Group 1 - Ordinary Grades

1.01- Mixed paper and board, unsorted, but unusable materials removed

A mixture of various grades of paper and board, without restriction on short fibre content.

1.02- Mixed papers and board (sorted)

A mixture of various qualities of paper and board, containing a maximum of 40% of newspapers and magazines.

1.03- Grey board

Printed and unprinted white lined and unlined grey board or mixed board, free from corrugated material.

1.04- Supermarket corrugated paper and board

Used paper and board packaging, containing a minimum of 70% of corrugated board, the rest being solid board and wrapping papers.

1.05- Old corrugated containers

Used boxes and sheets of corrugated board of various qualities.

1.06- Unsold magazines

Unsold magazines, with or without glue.

1.06.01- Unsold magazines without glue

Unsold magazines without glue.

Group 1 - Ordinary Grades



1.07 - Telephone Books

New and used telephone books, with unlimited content of pages coloured in the mass, with and without glue. Shavings allowed.

1.08- Mixed newspapers and magazines I

A mixture of newspapers and magazines, containing a minimum of 50% of newspapers, with or without glue.

1.09- Mixed newspapers and magazines II

A mixture of newspapers and magazines, containing a minimum of 60% of newspapers, with or without glue.

1.10 - Mixed magazines and newspapers

A mixture of newspapers and magazines, containing a minimum of 60% of magazines, with or without glue.

1.11- Sorted graphic paper for deinking

Sorted graphic paper from households, newspapers and magazines each at a minimum of 40%. The percentage of non- deinkable paper and board should be reduced over time to a maximum level of 1.5%. The actual percentage is to be negotiated between buyer and seller.



Group 2 - Medium Grades

2.01- Newspapers

Newspapers containing a maximum of 5% of newspaper or advertisements coloured in the mass.

2.02- Unsold Newspapers

Unsold daily newspaper, free from additional inserts or illustrated material coloured in the mass.

2.02.01- Unsold newspapers, no flexographic printing allowed

Unsold daily newspapers, free from additional inserts or illustrated material coloured in the mass, strings allowed. No flexographic printed material allowed.

2.03- Lightly printed white shavings

Lightly printed white shavings, mainly mechanical pulp-based paper.

2.03.01- Lightly printed white shavings without glue

Lightly printed white shavings, mainly mechanical pulp-based paper, without glue.

2.04- Heavily printed white shavings

Heavily printed white shavings, mainly mechanical pulp-based paper.

2.04.01 - Heavily printed white shavings without glue

Heavily printed white shavings, mainly mechanical pulp-based paper, without glue.

Group 2 - Medium Grades

2.05- Sorted office paper

Sorted office paper.

2.06- Coloured letters

Correspondence, in mixed papers coloured in the mass with or without print, of printing or writing paper, Free from carbon and hard covers.

2.07- White woodfree books

Books, including misprints of books, without hard covers, mainly of woodfree white paper, black printed only. Containing a maximum of 10% of coated paper.

2.08 - Coloured woodfree magazines

Coated or uncoated magazines, white or coloured in the mass, free from non-flexible covers, bindings, non dispersible inks and adhesives, poster papers, labels or label trim. May include heavily printed circulars and coloured in the mass shavings. Containing a maximum of 10% mechanical pulp-based papers.

2.11- Other PE-coated board

Other PE-coated board. May contain unbleached board and paper from board manufacturers and converters.

2.12- Mechanical pulp-based computer print-out

Continuous computer print-out, mechanical pulp based, sorted by colours, may include recycled fibres.



Group 3 - High Grades

3.01- Mixed lightly coloured printers shavings

Mixed shavings of printing and writing papers, lightly coloured in the mass, containing a minimum of 50% of woodfree paper.

3.02- Mixed lightly coloured woodfree printer shavings.

Mixed shavings of printing and writing papers lightly coloured in the mass, containing a minimum of 90% of woodfree paper.

3.03- Woodfree binders

White woodfree lightly printed shavings with glue, free from paper coloured in the mass. May contain a maximum of 10% of mechanical pulp-based paper.

3.04- Tear white shavings

White woodfree lightly printed shavings with glue, free from wet-strength paper and paper coloured in the mass.

3.05- White woodfree letters

Sorted white woodfree writing papers, originating from office records, free from cash books, carbon paper and non-water-soluble adhesives.

3.06- White business forms

White woodfree printed business forms

3.07 - White woodfree computer print-out

White woodfree computer print-out, free carbonless paper and glue.



3.08- Printed bleached sulphate board

Heavily printed sheets of bleached sulphate board, without glue, polycoated or waxed materials.

3.09- Lightly printed bleached sulphate board

Lightly printed sheets of bleached sulphate board, without glue, polycoated or waxed materials.

3.10- Multi printing

Woodfree, coated, lightly printed, free form wet strength paper or paper coloured in the mass.

3.11 - White heavily printed multiply board

New cuttings of heavily printed white multi-ply board containing woodfree, mechanical or thermos-mechanical pulp plies, but without grey plies.

3.12- White lightly printed multiply board

New cuttings of lightly printed white multi-ply board, containing woodfree, mechanical or thermos- mechanical pulp plies, but without grey plies.

3.13- White unprinted multiply board

New cuttings of unprinted white multi-ply board, containing woodfree, mechanical or thermos-mechanical pulp plies, but without grey plies.

3.14 - White newsprint

Shavings and sheets of white unprinted newsprint free from magazine paper.



3.15- White mechanical pulp based coated and uncoated paper

Shavings and sheets of white unprinted coated and uncoated mechanical pulp-based paper.

3.15.01- White mechanical pulp-based paper containing coated paper

Shavings and sheets of white unprinted mechanical pulp based coated paper.

3.16- White woodfree coated paper, without glue

Shavings and sheets of white unprinted woodfree coated paper, without glue.

3.17 - White shavings

Shavings and sheets of white unprinted paper, free from newsprint and magazine paper containing a minimum of 10% of coated paper. Without glue.

3.18- White woodfree shavings

Shavings and sheets of white unprinted woodfree paper; may contain a maximum of 5% of coated paper. Without glue.

3.18.01 - White woodfree uncoated shavings

Shavings and sheets of white unprinted woodfree paper, free from coated paper. Without glue.

3.19 - Unprinted bleached sulphate board

Unprinted sheets of bleached sulphate board, without glue, polycoated or waxed materials.



Group 4 - Kraft Grades

4.01- New shavings of corrugated board

Shavings of corrugated board, with liners of kraft or testliner

4.01.01 - Unused corrugated kraft

Unused boxes, sheets and shavings of corrugated board, with kraft liners only, the fluting made from chemical or thermo-chemical pulp.

4.01.02- Unused corrugating material

Unused boxes, sheets and shavings of corrugated board, with liners of kraft or testliner.

4.02- Used corrugated kraft I

Used boxes of corrugated board, with kraft liners only, the fluting made from chemical or thermo-chemical pulp.

4.03- Used corrugated kraft II

Used boxes of corrugated board, with liners of kraft or testliners.

Group 4 - Kraft Grades



4.04 - Used kraft sacks

Clean used kraft sacks. Wet-strength and non wet-strength.

4.04.01- Used kraft sacks with polycoated papers

Clean used kraft sacks. Wet-strength and non-wet strength. May include polycoated papers.

4.05 - Unused kraft sacks

Unused kraft sacks. Wet-strength

4.05.01- Unused kraft sacks with polycoated papers

Unused kraft sacks. Wet-strength and non-wet-strength may include polycoated papers.

4.06- Used kraft

Used kraft paper and board of a natural or white shade

4.07 - New Kraft

Shavings and other new kraft paper and board of a natural shade

4.08 - New carrier kraft

New carrier kraft, may include wet-strength paper.

Group 5 - Special Grades



5.01- Mixed recovered paper and board

Unsorted paper and board, separated at source.

5.02 - Mixed packaging

A mixture of various qualities of used paper and board packaging, free from newspaper and magazines.

5.03- Liquid board packaging

Used liquid packaging board including used PE-coated liquid packaging board (with or without aluminium content), containing a minimum of 50% by weight of fibres, and the balance being aluminium or coatings.

5.04- Wrapper Kraft

Poly-lined, sprayed, or laminated used kraft. Must not contain bitumen or wax coatings.

5.05- Wet labels

Used wet labels from wet-strength papers, containing a maximum of 1% glass content, and maximum of 50% moisture, without other unusable materials.

5.06 - Unprinted white wet - strength woodfree papers

Unprinted white wet -strength woodfree papers.

5.07- Printed white wet-strength woodfree papers

Printed white wet-strength woodfree papers.